

# Belzona 1523

FN10150



## INSTRUCTIONS FOR USE

### 1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

#### METALLIC SURFACES – APPLY ONLY AFTER BLAST CLEANING

- Brush away any loose contamination and remove dirt, oil, grease etc., with **Belzona® 9111** (Cleaner/Degreaser), or any other effective cleaner which does not leave a residue e.g. methyl ethyl ketone (MEK).
- Select an abrasive to give the necessary standard of cleanliness and a minimum depth of profile of 3 mils (75 microns). Use only an angular abrasive with low chloride content.
- Blast clean the metal surface to achieve the following standard of cleanliness:-  
ISO 8501-1 SA 2½ – very thorough blast cleaning  
American Standard Near White Finish SSPC SP10  
Swedish Standard SA2½ SIS 05 5900
- After blasting, metal surfaces should be coated before any contamination of the surface takes place.

#### NOTE: SALT CONTAMINATED SURFACES

The soluble salt contamination of the prepared substrate, immediately prior to application, shall be less than 20mg/m<sup>2</sup> (2µg/cm<sup>2</sup>).

Metal surfaces that have been immersed for any periods in salt solutions e.g. sea water, should be blasted to the required standard, left for 24 hours to allow the ingrained salts to sweat to the surface, then washed prior to a further brush blast to remove these. This process may need to be repeated several times to ensure complete removal of the salts. Salt removal aids are commercially available that will assist and speed salt removal. Contact Belzona for best recommendation.

### 2. PIT FILLING & STRIPE COATING

All welds should be prepared to NACE SP0178 Grade C or better. Deep pitting and rough welds should be smoothed out with **Belzona® 1511** mixed, applied and overcoated in accordance with the relevant IFU.

All detail areas such as welds, brackets, baffles, deflectors etc. that cannot be effectively sprayed should be stripe coated by brush with **Belzona® 1593**.

### 3. COMBINING THE REACTIVE COMPONENTS FOR HEATED AIRLESS SPRAY

Only commence mixing once the spray equipment has been assembled and thoroughly tested - see "Instructions for spraying Belzona solvent free coatings".

#### WORKING LIFE

From the commencement of mixing, **Belzona® 1523** must be used within the times shown:

| Temperature             | 68°F<br>(20°C) | 86°F<br>(30°C) | 104°F<br>(40°C) | 122°F<br>(50°C) |
|-------------------------|----------------|----------------|-----------------|-----------------|
| Use all material within | 45 mins.       | 35 mins.       | 25 mins.        | 15 mins.        |

### 4. APPLYING BELZONA® 1523

#### FOR BEST RESULTS

##### Do not apply when:-

- The substrate temperature is below 50°F (10°C), above 104°F (40°C) or the relative humidity is above 85%.
- The substrate temperature is less than 5°F (3°C) above dewpoint.
- Rain, snow, fog or mist is present.
- There is moisture on the metal surface or is likely to be deposited by subsequent condensation.
- The working environment is likely to be contaminated by oil or grease from adjacent equipment or from smoke from kerosene heaters.

#### 4.1 EQUIPMENT REQUIRED

**Belzona® 1523** must be sprayed using heated airless equipment. Either a single airless pump or plural equipment capable of metering accurately and mixing the two components can be used. See "Instructions for spraying Belzona solvent free coatings".

Mix ratio **4.5:1 by volume**  
Tip Temperature **104-122°F (40-50°C)**  
Tip pressure (minimum) **2500 psi (172 bar)**  
Tip size 17-23 thou **(0.43-0.58mm)**

#### DO NOT THIN

Cleaning solvent **Belzona® 9121, MEK or Acetone**

#### 4.2 COVERAGE RATES

|                                                                           |                                          |
|---------------------------------------------------------------------------|------------------------------------------|
| Recommended number of coats                                               | 2                                        |
| Target thickness 1 <sup>st</sup> coat                                     | 15 mils (375 microns)                    |
| Target thickness 2 <sup>nd</sup> coat                                     | 15 mils (375 microns)                    |
| Minimum total DFT                                                         | 20 mils (500 microns)                    |
| Maximum total DFT                                                         | 40 mils (1000 microns)                   |
| Maximum system DFT in stripe coat or repair areas                         | 60 mils (1500 microns)                   |
| Theoretical coverage rate 1 <sup>st</sup> coat                            | 28.7 sq.ft. (2.67 m <sup>2</sup> )/litre |
| Theoretical coverage rate 2 <sup>nd</sup> coat                            | 28.7 sq.ft. (2.67 m <sup>2</sup> )/litre |
| Theoretical coverage rate to achieve minimum recommended system thickness | 21.5 sq.ft. (2 m <sup>2</sup> )/litre    |

#### 4.3 PRACTICAL COVERAGE RATES

Appropriate loss factors must be applied to the above coverage rates. In practice, many factors influence the actual coverage rate achieved. On rough surfaces such as pitted steel the practical coverage rate will be reduced. Application at low temperatures will also reduce practical coverage rates further.

#### 4.4 OVERCOAT TIMES

The **Belzona® 1523** can be overcoated as soon as it is firm enough to do so. At 68°F (20°C) it will be possible to walk on the coating after 6-8 hours, but if access can be gained without walking on the first coat, overcoating can take place after as little as 3-4 hours. The maximum overcoat time is dependent on both temperature and humidity as set out below. After this time the surface must be brush blasted to achieve a frosted appearance free of gloss with a minimum surface profile of 40 microns.

| Temperature        | <50%<br>Relative Humidity | >50%<br>Relative Humidity |
|--------------------|---------------------------|---------------------------|
| Up to 68°F (20°C)  | 24 hours                  | 24 hours                  |
| Up to 86°F (30°C)  | 24 hours                  | 18 hours                  |
| Up to 104°F (40°C) | 18 hours                  | 8 hours                   |

#### 4.5 INSPECTION

- Immediately after application of each unit, visually inspect for pinholes and misses. Where detected, these should be immediately brushed out.
- Once the application is complete and the coating is dimensionally stable, carry out a thorough visual inspection to confirm freedom from pinholes and misses, and to identify any possible mechanical damage.
- Spark testing in accordance with NACE SP0188 can be carried out to confirm coating continuity. A voltage of 3kV is recommended to confirm that a minimum coating thickness of 20 mil (500 microns) has been achieved.

#### 4.6 REPAIRS

Within the overcoating window any misses, pinholes or mechanical damage can be repaired by application of **Belzona® 1523 or 1593** direct to the **Belzona® 1523** surface. Outside of the overcoating window, the surface of the **Belzona® 1523** must be abrasive blasted or abraded to produce a frosted appearance, free of all gloss, before coating. A profile of 1.5 mils (40 microns) should be aimed for.

#### 4.7 COLOUR

**Belzona® 1523** is available in different colours to facilitate application and to prevent misses. These colours are for identification only and there will be some variation between batches. In service the colour of the applied product may change.

#### 4.8 CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. MEK or Acetone. Brushes, spray equipment and other application tools should be cleaned using a suitable solvent such as MEK or Acetone.

## 5. COMPLETION OF THE MOLECULAR REACTION

The coating should be allowed to cure as follows:

| Ambient temperature | Time until inspection | Time until full service | Time until post-cure (if required) |        |
|---------------------|-----------------------|-------------------------|------------------------------------|--------|
|                     |                       |                         | Dry                                | Wet    |
| 50°F (10°C)         | 45 hrs                | 7 days                  | 45 hrs                             | 85 hrs |
| 68°F (20°C)         | 11 hrs                | 25 hrs                  | 11 hrs                             | 18 hrs |
| 86°F (30°C)         | 7 hrs                 | 14 hrs                  | 7 hrs                              | 10 hrs |
| 104°F (40°C)        | 4 hrs                 | 9 hrs                   | 4 hrs                              | 6 hrs  |

Coated equipment can be transported after the material has achieved the 'inspection' level of cure.

Post-cure will generally be unnecessary as the coating will cure sufficiently at ambient temperature with full cure achieved in service. However, post-cure may be desirable to facilitate faster cure and quicker return to service (see below).

#### 5.1 POST-CURE

If post-cure is desirable, the coating should be heated to between 122°F (50°C) and 212°F (100°C) for a minimum of 1 hour.

The coating should be allowed to cure as detailed in the above table prior to a dry (e.g. hot air) or wet (e.g. steam and liquid media) post-cure. Wet post-cure can typically be achieved during return to service, provided that the temperature ramp rate does not exceed 54°F (30°C) per hour.

#### 5.1.1 POST-CURE FOR CHEMICAL CONTACT

Post-cure requirements for optimal chemical resistance will vary depending on service conditions. For general guidance please refer to the Chemical Resistance Chart (CRC). For specific applications please contact your Belzona representative to discuss requirements.

## HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2023 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are  
manufactured under an  
ISO 9001 Registered  
Quality Management System*

