

Product Specification Sheet

Belzona 1121 (Super XL Metal)

FN10224



General Information

Product Description:
A two-component paste grade system with extended working life for repairing and rebuilding machinery and equipment. Based on a silicon steel alloy blended with high molecular weight reactive polymers and oligomers. Also used as a high strength structural adhesive for bonding or for creation of irregular load bearing shims with good electrical insulation characteristics. Once cured, the repair is durable and fully machinable. For use in Original Equipment Manufacture or repair situations.

Application Areas:
When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- | | | |
|--------------------|-----------------|----------------------------------|
| - Shafts, | - Keyways | - Piping, pipeline, and pipework |
| - Hydraulic rams | - Engine blocks | - Flange faces |
| - Bearing housings | - Casings | |
| - Bushing fits | - Levelling | |

Application Information

Application Methods: Applicator, spatula

Application Temperature: The application should ideally occur from 41 °F to 86 °F (5 °C to 30 °C).

Working Life: The working life will vary according to application temperature. The usable life of mixed material will typically be 30 minutes at 86 °F (30 °C). Consult the Belzona IFU for specific details.

Volume Capacity: 23 in³/kg (374 cm³/kg)

Cure Times:
Cure times will vary depending on the ambient conditions and will be reduced for thicker sections and extended for thinner applications. Consult the Belzona IFU for specific details.

Base Component	
Appearance	Paste
Color	Dark grey
Gel Strength (4 cm ² paddle) at 22 °C	300 - 400 g/cm
Density	0.046 – 0.049 kg/in ³ (2.8 – 3.0 g/cm ³)
Solidifier Component	
Appearance	Paste
Color	Light grey
Gel Strength (8 cm ² paddle) at 22 °C	130 – 200 g/cm
Density	0.039 – 0.043 kg/in ³ (2.4 – 2.6 g/cm ³)
Mixed Properties	
Mixing Ratio by Weight (Base: Solidifier)	1.2: 1
Mixing Ratio by Volume (Base: Solidifier)	1: 1
Mixed Form	Paste
Peak Exotherm Temperature	86 - 104 °F (30 - 40 °C)
Time to Peak Exotherm	60 – 80 min.
Mixed Density	0.043 – 0.044 kg/in ³ (2.6 – 2.7 g/cm ³)
Slump Resistance	Nil at 1.0 in. (2.5 cm)
VOC Content (ASTM D2369/EPA Ref. 24)	0.05% (1.29 g/L)

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

Product Specification Sheet

Belzona 1121 (Super XL Metal)

FN10224



Abrasion

Taber

When tested in accordance with ASTM D4060 (1-kg load), the sliding abrasion of samples cured under the conditions stated below (per 1,000 cycles) will typically be:

CS17 Wheels (Dry)	66 mm ³ loss – 72 °F (22 °C) cure
H10 Wheels (Wet)	1,345 mm ³ loss – 72 °F (22 °C) cure

Adhesion

Cleavage

When tested in accordance with ASTM D1062, the cleavage adhesion of Belzona 1121 applied onto samples abrasive-blasted to an average surface profile of 3 mil (75 µm) and cured at 72 °F (22 °C) for 7 days will typically be:

Carbon steel	1,050 lbf/in. (18.8 kgf/mm)
--------------	-----------------------------

Tensile Shear

When tested in accordance with ASTM D1002, the tensile shear of Belzona 1121 applied onto samples abrasive-blasted to an average surface profile of 3 mil (75 µm) and cured at 72 °F (22 °C) for 7 days will typically be:

Aluminum	2,500 psi (17.2 MPa)
Carbon steel	3,500 psi (24.1 MPa)
Copper	2,600 psi (17.9 MPa)

Pull Off

When tested in accordance with ASTM D4541/ISO 4624, the pull-off adhesion of Belzona 1121 applied onto steel samples blasted to an average surface profile of 3 mil (75 µm) and cured at 72 °F (22 °C) for 7 days will typically be:

2,800 psi (19.3 MPa)

Chemical Analysis

The mixed Belzona 1121 has been independently analyzed for halogens, heavy metals, and other corrosion-causing impurities in accordance with ASTM E165, ASTM D4327 and ASTM E1479. Typical results are displayed as follows:

Analyte	Total Concentration (ppm)
Fluoride	205
Chloride	251
Bromide	< 49
Sulfur	18,877
Nitrile	< 6
Nitrate	< 10
Zinc	7
Antimony, Arsenic, Bismuth, Cadmium, Lead, Tin, Silver, Mercury, Gallium, and Indium	ND (< 4)

ND: Not Detected

Chemical Resistance

When fully cured, the material will demonstrate excellent resistance to a broad range of chemicals. For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.

Compressive Properties

When tested in accordance with ASTM D695, the compressive properties of samples cured at 72 °F (22 °C) for 7 days will typically be:

Compressive Strength

9,000 psi (62.0 MPa)

Compressive Modulus

4.6 x 10⁵ psi (3.2 GPa)

Corrosion Protection

Upon full curing at 72 °F (22 °C) for 7 days, Belzona 1121 will show no visible signs of corrosion after 1,000 hours of salt spray exposure in accordance with ASTM B117.

Flexural Properties

When tested in accordance with ASTM D790, the flexural strength and strain-at-break of samples cured at 72 °F (22 °C) for 7 days will typically be:

Flexural Strength

7,000 psi (48.3 MPa)

Flexural Strain at Break

0.62%

Hardness

Barcol

When tested in accordance with ASTM D2583 and using a Barcol impressor Model No. 935, the hardness of samples cured at 72 °F (22 °C) for 7 days will typically be:

85

Shore D

When tested in accordance with ASTM D2240, the Shore D hardness of samples cured at 72 °F (22 °C) for 7 days will typically be:

85

Product Specification Sheet

Belzona 1121 (Super XL Metal)

FN10224



Heat Resistance

Glass Transition Temperature (T_g)

When tested to ISO 11357-2, T_g of samples cured at 72 °F (22 °C) for 7 days will typically be:

130 °F (54 °C)

Service Temperature Limits

For many applications, the product will be suitable for use at the following service temperatures:

Type of Service	Temperature
Lower temperature limit	-40 °C (-40 °F)
Upper temperature limit (dry)	60 °C (140 °F)
Upper temperature limit (wet)	50 °C (122 °F)

Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO 11357 is typically 392 °F (200 °C).

Shelf Life

Separate base and solidifier components shall have a shelf life of five (5) years from date of manufacture when stored in their original unopened containers between 41 °F (5 °C) and 86 °F (30 °C).

Impact Resistance

Izod Pendulum

When tested in accordance with ASTM D256, the impact (un-notched) resistance of samples cured at 72 °F (22 °C) for 7 days will typically be:

1.23 ft-lb/in (65.9 J/m)

Tensile Properties

When determined in accordance with ASTM D638, typical values of samples cured and tested at 72 °F (22 °C) for 7 days will be:

Ultimate Tensile Strength	3,185 psi (22.0 MPa)
Young's Modulus	7.9×10^5 psi (5.4 GPa)

Approvals

American Bureau of Shipping

Belzona 1121 holds "Product Type Approval" by ABS under certificate number 23-2426036-PDA.

Contact Belzona for more details on these approvals or any other approvals or certifications not stated herein.

Product Specification Sheet

Belzona 1121 (Super XL Metal)

FN10224



Warranty

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information for Use (IFU) leaflet.

Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO etc.).

Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

Availability and Cost

Belzona 1121 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

Health and Safety

Prior to using this material, please consult the relevant Material Safety Data Sheets.

Manufacturer/Supplier

Belzona Polymerics Limited
Claro Road
Harrogate HG1 4DS
United Kingdom

Belzona, Inc.
14300 NW 60th Ave,
Miami Lakes, FL, 33014, USA

Technical Service

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development, and quality control laboratories.

The technical data contained herein is based on the results of long-term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose. Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2023 Belzona International Limited. Belzona® is a registered trademark.

**Belzona products are
manufactured under an ISO
9001 registered Quality
Management System.**

