

Surface and Anti-Corrosion Coating

Zinc-Alu-Spray



Anti-corrosion protection | colour shade matching hot-dip galvanization

WEICON Zinc-Alu Spray permanently protects all metal surfaces against rust and corrosion. It forms a fast-drying and adherent protective layer and is resistant to many chemicals. Zinc-Alu Spray can be used for repairing hot galvanized parts with matching colours and for the coating of welded joints and drill holes.

Technical data

Application range	indoor and outdoor use	
Binder	Acrylate resin	
Pigment	zinc and aluminium pigments	
Pigment purity	approx. 99.5% Al / ca. 94.0% Zn	
Metal content in dry film	~51 %	
Processing temperature	+5 °C to +35 °C, ideally +18 °C to +35 °C	
Recommended primer	Zinc Spray	
Consumption	per 1.5 crosswise application	~ 2 m ²
Layer thickness with 1.5 crosswise applications approx.	20 - 40 µm	
Dust-dry after	15 min.	
Minimum shelf life	at room temperature	24 mon.
Cured after	10-12 h	
Grid cut	DIN 53151/ISO 2409	Cross cutting test value 0 to 1
Mandrel bending test	DIN EN ISO 1519	no hairline cracking
Top coat	not required	
Density	0,9 g/cm ³	
Temperature resistance	-50°C to +300°C	

Approvals / Guidelines

IKS	DIN EN ISO 9227-NSS / 504 hours
-----	---------------------------------

Surface Pre-Treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

Processing

Shake can before use until the mixing ball can be heard clearly. Spray on evenly and crosswise at room temperature (approx. 20°C) and at about 25 cm distance from the surface. Dust-dry after approx. 15 minutes, fully hardened after approx. 10-12 hours.

Storage

Pressurized container. Protect from direct sunlight and temperatures above +50°C.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes

1000048	Zinc-Alu-Spray, 400 ml
10059902	Zinc-Alu-Spray, 400 ml

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 10 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr