

TORAYCA® T300 DATA SHEET

Baseline carbon fiber used in aerospace applications. Has 30 year production history and is known for its balanced composite properties, high quality, consistency, reliability and supplyability.

FIBER PROPERTIES

		English	Metric	Test Method
Tensile Strength		512 ksi	3,530 MPa	TY-030B-01
Tensile Modulus		33.4 Msi	230 GPa	TY-030B-01
Strain		1.5 %	1.5 %	TY-030B-01
Density		0.064 lbs/in ³	1.76 g/cm ³	TY-030B-02
Filament Diameter		2.8E-04 in.	7 μm	
Yield	1K	22,568 ft/lbs	66 g/1000m	TY-030B-03
	3K	7,523 ft/lbs	198 g/1000m	TY-030B-03
	6K	3,761 ft/lbs	396 g/1000m	TY-030B-03
	12K	1,862 ft/lbs	800 g/1000m	TY-030B-03
Sizing Type & Amount	40A, 40B		1.0 %	TY-030B-05
	40D		0.7 %	TY-030B-05
	50A, 50B		1.0 %	TY-030B-05
	Twist	Twisted, Untwisted, or Never twisted		

FUNCTIONAL PROPERTIES

GTE	-0.41 α-10 ⁻⁶ /°C
Specific Heat	0.19 Cal/g·°C
Thermal Conductivity	0.025 Cal/cm·s·°C
Electric Resistivity	1.7 x 10 ⁻³ Ω·cm
Chemical Composition: Carbon	93 %
	Na + K

COMPOSITE PROPERTIES*

Tensile Strength	270 ksi	1,860 MPa	ASTM D-3039
Tensile Modulus	20.0 Msi	135 GPa	ASTM D-3039
Tensile Strain	1.3 %	1.3 %	ASTM D-3039
Compressive Strength	215 ksi	1,470 MPa	ASTM D-695
Flexural Strength	260 ksi	1,810 MPa	ASTM D-790
Flexural Modulus	18.0 Msi	125 GPa	ASTM D-790
ILSS	14 ksi	10 kgf/mm ²	ASTM D-2344
90° Tensile Strength	11.0 ksi	76 MPa	ASTM D-3039

* Toray 250°F Epoxy Resin. Normalized to 60% fiber volume.

TORAY CARBON FIBERS AMERICA, INC.